



Made in the  
United States of America



## Description

Conductive Drum Liners 2014 do not hold static charge when grounded. The drum liners are constructed from a single layer of carbon loaded polyethylene. The material is non-sloughing, and does not contaminate components it comes in contact with, despite repeated use.

## Specifications

### Properties

Properties	Test Method	Value
Thickness		4.0 mil (0.0040", 0.1016mm)
Color		Black Opaque
Tensile Strength	ASTM D882	MD >2,000 psi
Elongation	ASTM D882	MD 150%
Dart Impact	ASTM D1709	250 to 700 grams @ 26" drop
Tear Strength	ASTM D882	>400 lbs/in.
Mullen Burst	AST D774	20 - 60 PSI
Puncture	FED Std 101	8 lbs

### Electrical Properties

Electrical Properties	Test Method	Value
Volume Resistivity	ASTM D991	< 30,000 Ohms/cm
Surface Resistivity	ASTM D257	< 30,000 Ohms/sq

### Heat Sealing

Temperature	250 - 375°F
Time	0.5 - 3.5 sec
Pressure	30 - 70 PSI

### Chemical Susceptibility ASTM D543

Dilute Acids and Alkalies	Resistant
Alcohols (Isopropanol)	Resistant
Hydrocarbons (Acetone)	Moderate Attack
Ketones (Acetone)	Slight Attack
Gasoline	Moderate Attack
Aromatic Hydrocarbons (Toluene)	Severe Attack

Item	Size	Gallon Size	Quantity
<a href="#">2014 18X24</a>	18" x 24"	5	100 / Box
<a href="#">2014 38X58</a>	38" x 58"	55	50 / Box

Unless specified tolerance is  $\pm 10\%$

Specifications and procedures subject to change without notice.

## VELOSTAT® CONDUCTIVE DRUM LINER

# PROTEKTIVE PAK

PROTEKTIVE PAK  
13520 MONTE VISTA AVENUE, CHINO, CA 91710  
PHONE (909) 627-2578  
[ProtektivePak.com](http://ProtektivePak.com)

DRAWING  
NUMBER  
2014 18X24

DATE  
February  
2017